



EGE KİMYA A.Ş.

HEADQUARTERS

Cendere Yolu No. 16-18
Kağıthane 80350
İSTANBUL / TÜRKİYE
Tel : (0-212) 294 65 67 -74
Fax : (0-212) 294 52 98
e-posta/e-mail : info@egekimya.com

FACTORY

Aşağı Kirazca Mevkii, Nehirkent
ADAPAZARI / TÜRKİYE
Tel : (0-264) 229 32 00 - 09
Fax : (0-264) 229 38 54 -55



TS-EN-ISO-9001

EGELub 50

PRODUCT DATA

Properties :

Egelub 50 is a water dispersible powder that consist of a combination of silicates, fatty acid esters and special anti-adhesives.

Physical and chemical properties :

(Typical values)

Appearance	White to yellow powder
pH (in a 2.5% sol.)	9.5
Volatiles Matter, 105°C,%	3
Ignition Loss (1000°C),%	44
Bulk Density (g/lt)	370

Application fields are :

Egelub 50 is applicable as 2.5 - 5 % in aqueous solution. Agitation at 60-70°C in the mixing tank for 1 hour before using and during batch-off is recommended.

Packaging :

Kraft bag.

Expiry data :

One year from production date.

APPLICATION :

The common usage levels are around 2.5 - 5 % based on rubber type used (SBR, butyl, NR, EPDM, etc.). Agitation is required during preparation and batch-off.

SAFETY DATA

CAS No : Preparation

Hazard Identification :

Not classified as hazardous.

Handling and Storage :

Handling precautions	: Avoid eye contact. Avoid formation of dust during use.
Technical protection equipment	: Dust extraction in areas of dust formation.
Storage	: Store dry. Protect againts humidity.
Incompatibilities	: None known
Unsuitable packaging material	: None known.
Further information	: None.

Transport Information :

UN - No : Not applicable.
Road & rail Transport (ADR/RID) : Not applicable.
GGVSee/IMDG - Code : Not applicable.
Air Transporter (ICAO) : Not applicable. No special transportation codes.

Rev. T. / No: 27.11.2002/000

The above information has been compiled to the best of our knowledge. The use and application of this information

is at the user's sole risk and discretion. Ege Kimya as will not accept any responsibility.

