

# EGE KİMYA A.Ş.

## HEADQUARTERS

Cendere Yolu No. 16-18  
Kağıthane 80350  
İSTANBUL / TÜRKİYE  
Tel : (0-212) 294 65 67 -74  
Fax : (0-212) 294 52 98  
e-posta/e-mail : info@egekimya.com

## FACTORY

Aşağı Kirazca Mevkii, Nehirkent  
ADAPAZARI / TÜRKİYE  
Tel : (0-264) 229 32 00 - 09  
Fax : (0-264) 229 38 54 -55



TS-EN-ISO-9001

## 8030

### PRODUCT DATA

#### **Definition of the product**

Hot Water Tank Enamel (medium component)

#### **Properties :**

Physical state	solid
Shape	flake
Firing temperature (C)	830±10
Melting point/range (C)	500
Bulk density (gr/cm <sup>3</sup> )approx.	1.15
(ISO 2744) water (gr/m <sup>2</sup> day)	1,20±0,80
(ISO 2744) vapour (gr/m <sup>2</sup> day)	3,0±1,50

#### **Application fields are :**

Water tanks, boilers, washing machines, dish washers

#### **Packaging :**

25 kgs.bags craft paper

#### **Expiry data :**

Unlimited in dry and clean area

#### **APPLICATION :**

Applied on pre-treated enamel quality sheet steel. Usually used in combination with 8029 and 8031  
The percentage in the combination, can vary in accordance with the conditions of users.

### SAFETY DATA

#### **Hazard Identification :**

Inflammable.

#### **Handling and Storage :**

**Handling :** Provide for sufficient ventilation at the working place.

**Storage :** Keep the product in a clean and dry area.

#### **Transport Information :**

ADR Class : Not applicable  
RID Class : Not applicable  
IMDG Class : Not applicable  
IATA Class : Not applicable

